



Allgemeine  
Bauaufsichtliche  
Zulassung Z-70.3-254  
Gutachten: G-70-20-0004 (VSG)  
Gutachten: G-70-19-0002 (Schubverbund)

# Saflex® Structural PVB interlayer

*High-performance laminate designed for strength*



Saflex® Structural interlayer is a tough polyvinyl butyral interlayer (PVB) designed for applications where interlayer rigidity and high glass adhesion requirements are not met with standard glazing interlayers. Saflex Structural provides superior structural capacity compared with standard PVB interlayers. In properly designed systems, Saflex Structural is capable of keeping glass intact at high and low temperatures after impact and under load. It's formulated to provide robust resistance to delamination and excellent edge stability and is compatible with visibly reflective coatings and low-emissivity coatings.

Saflex Structural glazing is suitable for exposed edge laminates, floors, stairs, balconies, canopies, point glazing systems, clip systems, captured systems, curtain walls, and sloped and overhead glazing where glass needs to remain intact after breakage.

Due to the stiffness of Saflex Structural interlayer, laminates can either sustain higher uniform loads with the same glass thickness or the glass thickness can be reduced and still achieve the same loading. Saflex Structural can be used with annealed, heat-strengthened, and fully tempered glass. Glass selection should be based on required performance attributes such as load requirements, optical distortion, potential for spontaneous breakage, thermal stress capability, stress capability, and post-breakage performance such as glass shard retention, viewing, and the ability to withstand limited load.

## Benefits

- **Post-breakage safety**  
Higher load capability sustains safety after breakage.
- **Superior edge stability**  
Enhances delamination resistance
- **Enhanced unit strength**  
Facilitates oversized glass design
- **Enhanced interlayer strength**  
Enables thinner glass to reduce weight and cost
- **Superwide 3.2 m width**  
Improves throughput and reduces costs
- **Vanceva® Colors compatibility**  
Creates thousands of color opportunities



## Do you need to run glass stress calculations?

Visit [www.saflex.com/tools](http://www.saflex.com/tools), and start using Saflex StructuralPro. The software will perform calculations and provide a PDF report via email, detailing:

- Load resistance
- Glass stress
- Deflection for the requested configuration
- Effective thickness for the single-unit laminate from which the model was generated
- Overall thickness and weight of the glass

## Saflex® Structural product offering

Product nomenclature	Thickness	Std. widths	Std. lengths	Transparency
Saflex® DG	0.76 mm (0.030 in.)	45–322 cm	250 m	Clear

## Saflex® Structural mechanical and physical properties

Technical data	Property	Test method	Units	Test conditions	Saflex® Structural interlayer	
Physical	Specific heat	ASTM E1269	J/kg°C	28°–80°C	2150	
	Specific gravity	ASTM D792	g/cm³	—	1.09	
	Hardness	ASTM D2240	Shore D	Cut/stacked to 12.5 mm	52	
Mechanical	Elongation at failure	JIS K6771	%	23°C/50% RH	190	
	Tensile strength	JIS K6771	kg/cm	23°C/50% RH	330	
	Tear strength	ASTM D624	N/mm	23°C/50% RH	106	
	Poisson's ratio	ASTM D638	—	23°C/50% RH	0.476	
Thermal	Coefficient of thermal expansion	ASTM D831	10 <sup>-6</sup> /°C	–18° to 30°C	129 x 10 <sup>-6</sup>	
	Thermal conductivity, K	ASTM F5930	W/m/(m²°C)	36°C	0.196	
					DG	DG XC
Solar	Solar transmittance	NFRC 300	D65	Clear 3-mm glass	76%	76%
	Visible transmittance	NFRC 300	D65	Clear 3-mm glass	89%	88%
	UV screening	NFRC 300	280–380 nm	Clear 3-mm glass	>99%	>99%

Note: The designed high adhesion may render this product inappropriate for lamination with thin annealed lites of glass when used as a single-layer interlayer where penetration resistance is required. Information regarding the safe handling and storage of Saflex Structural can be found in the Safety Data Sheet that is available from the Advanced Interlayers sales organization or at [www.Eastman.com](http://www.Eastman.com).

### Additional benefits of Saflex laminated glass



Safety protection



Burglary protection



Storm protection



UV protection



Noise reduction

### Architects and designers trust Saflex®.

Around the world, architects and designers trust Saflex when performance and safety are their most critical concerns. The reason for their confidence is simple. No matter what the specifications or performance targets, Saflex interlayer technology delivers advanced glazing performance for demanding applications.



# EASTMAN

The results of insight.

#### Eastman Corporate Headquarters

P.O. Box 431  
Kingsport, TN 37662-5280 U.S.A.

U.S.A. and Canada, 800-EASTMAN (800-327-8626)  
Other Locations, +(1) 423-229-2000

[www.eastman.com/locations](http://www.eastman.com/locations)

Although the information and recommendations set forth herein are presented in good faith, Eastman Chemical Company ("Eastman") and its subsidiaries make no representations or warranties as to the completeness or accuracy thereof. You must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. Nothing contained herein is to be construed as a recommendation to use any product, process, equipment, or formulation in conflict with any patent, and we make no representations or warranties, express or implied, that the use thereof will not infringe any patent. NO REPRESENTATIONS OR WARRANTIES, EITHER EXPRESS OR IMPLIED, OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR OF ANY OTHER NATURE ARE MADE HEREUNDER WITH RESPECT TO INFORMATION OR THE PRODUCT TO WHICH INFORMATION REFERS AND NOTHING HEREIN WAIVES ANY OF THE SELLER'S CONDITIONS OF SALE.

Safety Data Sheets providing safety precautions that should be observed when handling and storing our products are available online or by request. You should obtain and review available material safety information before handling our products. If any materials mentioned are not our products, appropriate industrial hygiene and other safety precautions recommended by their manufacturers should be observed.

© 2020 Eastman. Eastman brands referenced herein are trademarks of Eastman or one of its subsidiaries or are being used under license. The ® symbol denotes registered trademark status in the U.S.; marks may also be registered internationally. Non-Eastman brands referenced herein are trademarks of their respective owners.